

Nakano et al.
U.S.S.N. 10/527,352
Page 3 of 14


RECEIVED
CENTRAL FAX CENTER

SEP 28 2007

IN THE CLAIMS:

This listing of claims will replace all prior versions of claims in the application.

1. (Currently amended) A polycarbonate-based resin composition for extrusion molding using a sizing die, the polycarbonate-based resin composition comprising as a main component, a polycarbonate having a viscosity-average molecular weight of 17000 to 27000 and containing main repeating units represented by the following formula (A):



wherein an amount of proton (Pa) and an amount of proton (Pb) per 1 g of the polycarbonate which are calculated from respective integral values of a signal (a) detected at $\delta = 7.96$ to 8.02 ppm and a signal (b) detected at $\delta = 8.11$ to 8.17 ppm in $^1\text{H-NMR}$ spectra thereof as measured in a deuterated chloroform solvent, satisfy the following formula (1):

$$4 < \{ (Pa) + (Pb) \} < 26 \quad (1)$$

wherein a unit of each of (Pa) and (Pb) is $\mu\text{mol/g}$.

2. (Original) A polycarbonate-based resin composition according to claim 1, wherein a ratio of an amount of proton (Pc) per 1 g of the polycarbonate which is calculated from an integral value of a signal (c) detected at $\delta = 10.35$ to 10.50 ppm in $^1\text{H-NMR}$ spectra thereof as measured in a deuterated chloroform solvent, to the amount of proton (Pa) $((Pc)/(Pa))$, and a ratio of the amount of proton (Pa) to the amount of proton (Pb) $((Pa)/(Pb))$, satisfy the following formulae (2) and (3), respectively:

$$0 < (Pc)/(Pa) < 0.5 \quad (2); \text{ and}$$

Nakano et al.
U.S.S.N. 10/527,352
Page 4 of 14

$$0.5 < (Pa)/(Pb) < 3 \quad (3)$$

wherein a unit of each of (Pa), (Pb) and (Pc) is $\mu\text{mol/g}$.

3. (Original) A polycarbonate-based resin composition according to claim 1 or 2, wherein the amount of proton (Pb) and the amount of proton (Pc) have a relationship represented by the following formula (4):

$$0.70 < (Pb)/\{(Pb) + (Pc)\} < 0.96 \quad (4)$$

wherein a unit of each of (Pb) and (Pc) is $\mu\text{mol/g}$.

4. (Original) A polycarbonate-based resin composition according to any one of claims 1 to 3, wherein the polycarbonate is produced by transesterification of an aromatic dihydroxy compound and a carbonic diester compound.

5. (Original) A polycarbonate-based resin composition according to any one of claims 1 to 4, further comprising at least one mold release agent in an amount of 0.001 to 5 parts by weight.

6. (Original) A polycarbonate-based resin composition according to claim 5, wherein the mold release agent is at least one compound selected from the group consisting of hydrocarbons, aliphatic carboxylic acids, aliphatic alcohols, esters of aliphatic carboxylic acids and alcohols, and polysiloxane-based silicone oils.

7. (Original) A molded product produced by extrusion-molding the resin composition as defined in any one of claims 1 to 6 using a sizing die.

Nakano et al.
U.S.S.N. 10/527,352
Page 5 of 14


8. (Original) A molded product according to claim 7, wherein the molded product is in the form of a twin-wall molded product or a molded product having three or more-layered walls.

9. (Original) A molded product according to claim 7 or 8, wherein the molded product is provided on at least a part of a surface thereof with a coating layer.

10. (Original) A molded product according to any one of claims 7 to 9, wherein the molded product is in the form of a laminate produced by integrally laminating a layer comprising other resin composition thereon by a co-extrusion method.

11. (Original) A molded product according to any one of claims 7 to 10, wherein the molded product is provided on at least a part of a surface thereof with a coating layer comprising the other resin composition, and the coating layer is integrally laminated thereon by a co-extrusion method.

12. (Original) A molded product according to claim 10 or 11, wherein the other resin composition is a polycarbonate resin composition comprising as a main component, a polycarbonate having a viscosity-average molecular weight of 17000 to 40000 and containing main repeating units represented by the following formula (A):



wherein an amount of proton (Pa) and an amount of proton (Pb) per 1 g of the polycarbonate which are calculated from respective integral values of a signal (a) detected at $\delta = 7.96$ to 8.02 ppm and a signal (b) detected at $\delta = 8.11$ to 8.17 ppm in

Nakano et al.
U.S.S.N. 10/527,352
Page 6 of 14

^1H -NMR spectra thereof as measured in a deuterated chloroform solvent, satisfy the following formula (x):

$$\{(Pa) + (Pb)\} < 26 \quad (x)$$

wherein a unit of each of (Pa) and (Pb) is $\mu\text{mol/g}$.

13. (Original) A molded product according to claim 10 or 11, wherein the other resin composition contains at least one ultraviolet absorber in an amount of 1 to 25 parts by weight.

14. (Original) A molded product according to claim 13, wherein the ultraviolet absorber is at least one compound selected from the group consisting of triazole-based compounds, triazine-based compounds, cyanoacrylate-based compounds and benzophenone-based compounds.

15. (Previously presented) A polycarbonate-based resin composition according to claim 2, wherein the amount of proton (Pb) and the amount of proton (Pc) have a relationship represented by the following formula (4):

$$0.70 < (Pb)/\{(Pb) + (Pc)\} < 0.96 \quad (4)$$

wherein a unit of each of (Pb) and (Pc) is $\mu\text{mol/g}$.

16. (Previously presented) A polycarbonate-based resin composition according to claim 2, wherein the polycarbonate is produced by transesterification of an aromatic dihydroxy compound and a carbonic diester compound.

Nakano et al.
U.S.S.N. 10/527,352
Page 7 of 14

17. (Previously presented) A polycarbonate-based resin composition according to claim 3, wherein the polycarbonate is produced by transesterification of an aromatic dihydroxy compound and a carbonic diester compound.

18. (Previously presented) A polycarbonate-based resin composition according to claim 2, further comprising at least one mold release agent in an amount of 0.001 to 5 parts by weight.

19. (Previously presented) A polycarbonate-based resin composition according to claim 3, further comprising at least one mold release agent in an amount of 0.001 to 5 parts by weight.

20. (Previously presented) A polycarbonate-based resin composition according to claim 4, further comprising at least one mold release agent in an amount of 0.001 to 5 parts by weight.

21. (Previously presented) A molded product according to claim 8, wherein the molded product is provided on at least a part of a surface thereof with a coating layer.

22. (Previously presented) A molded product according to claim 8, wherein the molded product is in the form of a laminate produced by integrally laminating a layer comprising another resin composition thereon by a co-extrusion method.

23. (Previously presented) A molded product according to claim 9, wherein the molded product is in the form of a laminate produced by integrally laminating a layer comprising another resin composition thereon by a co-extrusion method.


Nakano et al.
U.S.S.N. 10/527,352
Page 8 of 14

24. (Previously presented) A molded product according to claim 8, wherein the molded product is provided on at least a part of a surface thereof with a coating layer comprising another resin composition, and the coating layer is integrally laminated thereon by a co-extrusion method.

25. (Previously presented) A molded product according to claim 9, wherein the molded product is provided on at least a part of a surface thereof with a coating layer comprising another resin composition, and the coating layer is integrally laminated thereon by a co-extrusion method.

26. (Previously presented) A molded product according to claim 10, wherein the molded product is provided on at least a part of a surface thereof with a coating layer comprising another resin composition, and the coating layer is integrally laminated thereon by a co-extrusion method.

27. (Previously presented) A molded product according to claim 11, wherein said another resin composition is a polycarbonate resin composition comprising as a main component, a polycarbonate having a viscosity-average molecular weight of 17000 to 40000 and containing main repeating units represented by the following formula (A):



wherein an amount of proton (Pa) and an amount of proton (Pb) per 1 g of the polycarbonate which are calculated from respective integral values of a signal (a) detected at $\delta = 7.96$ to 8.02 ppm and a signal (b) detected at $\delta = 8.11$ to 8.17 ppm in

Nakano et al.
U.S.S.N. 10/527,352
Page 9 of 14

¹H-NMR spectra thereof as measured in a deuterated chloroform solvent, satisfy the following formula (x):

$$\{(Pa) + (Pb)\} < 26 \quad (x)$$

wherein a unit of each of (Pa) and (Pb) is $\mu\text{mol/g}$.

28. (Previously presented) A molded product according to claim 11, wherein said another resin composition contains at least one ultraviolet absorber in an amount of 1 to 25 parts by weight.